

ALLOY DATA SHEET



GE240

Visit our website
www.safe-metal.com



WHO ARE WE ?

Safe Metal is the world leader in steel components made by green sand casting. Our teams operate as part of an international network that stretches across Europe, America and Asia, and partner their sales and project management skills with those of their customers.

MAKING WORLD CLASS

Thanks to the expert skills of our R&D department, we are able to improve our industry knowledge and hence our products, our production process and metalworking by choosing the most appropriate methods for the product



GE240

Generality

Carbon-manganese steel with low manganese to be a soft magnetic steel. Good weldability.

Market : this alloy can be used in all markets.



Chemical Composition

C (%)	Si (%)	Mn (%)	P (%)	S (%)
0,18-0,25	0,3-0,6	0,8-1	<0,025	<0,025

Main characteristics

GE240

Family : Versatile

Weldability



Impact test values



Machining



Cost



Mechanical resistance



GE240

Mechanical characteristics & Heat treatment

Reference	Designation		Heat Treatment			Thickness	Mechanical properties				
	Name	Number	Symbol	Normalizing or austenitizing °C	Tempering °C	t mm	Tensile test at room temperature			Impact test	
							R _{p0.2} MPa min.	R _m MPa min.	A% min.	KV J min.	Temp. °C
Safe Metal possibilities according to norms :											
EN 10293:2015	GE240	1.0446	+N	900 to 980		t ≤ 300	240	450 to 600	22	27	RT
Safe Metal other possibilities :											
Safe Metal	GE240		+N	TN1		t ≤ 30	360	530	30	40	RT
Safe Metal	GE240		+QT HR		High Rm	t ≤ 30	400 to 450	600 to 650	25	60	RT
Safe Metal	GE240		+QT HD		High Kv	t ≤ 30	350 to 400	550 to 600	30	75	RT

RT : Room temperature

HR : High resistance


N : Normalized

QT : Liquid quenched and tempered


HD : High ductility

Microstructures


QUENCHING + TEMPERED AT 500°C



QUENCHING + TEMPERED AT 600°C



NORMALIZED



Machining


			HB*	Microstructure
EN 10293:2015	GE240	+N	130-180	Ferrite + Pearlite
Safe Metal	GE240	+N	150	Ferrite + Pearlite
Safe Metal	GE240	+QT HR	175-195	Bainite + Tempered Martensite
Safe Metal	GE240	+QT HD	160-175	Bainite + Ferrite + Pearlite

HB : Brinell hardness

GE240

Welding

Preheating conditions according to thickness and equivalent carbon. A specific zone is defined where preheating is not absolutely necessary and depends on the case.



Welding comparative table

Grade	Group (ISO TR 15608)	Filler Metal	Post-Welding HT	Hardness of melted area (Hv10)	Rm (MPa)	Process (acc. NFEN ISO 15614)
C steel						
G20	1.2	E71T5	SR/N	130-170	450-550	111/135
		E71T5	QT	150-200	550-650	
G20Mn5	1.2	E70C6 M H4	SR/N	150-200	500-550	
		E70C6 M H4	QT	160-220	540-580	
G24Mn6	3.1	ER110T5	SR	240-300	750-900	
		ER110T5	QT	260-340	780-950	
G28Mn6	3.1	ER80S02	SR			
		ER80S02	QT			
G30MnV6	3.1	ER110T5	SR	130-170	450-550	
		ER110T5	QT	150-200	550-650	
GE280	1.2	E70C6 M H4	SR/N	150-200	500-550	111
		E70C6 M H4	QT	160-220	540-580	
G20MnV6	3.1	ER110T5	SR	240-300	750-900	
		ER110T5	QT	260-340	780-950	
Cr-Mn						
G16CrMo4	5.1	E9018B3	SR	160-250	620-680	111/135
G25CrMo4	5.1	E12018G	QT	200-260	630-720	111/135
G30CrMo4	5.1	E12018G	QT	300-350	900-1150	111
G21Cr-MoV-11	6.2	E13018G	SR	280-330	800-1000	111
Others						
G10MnMoV6	3.1	ER90 S-G	SR	200-280	620-680	135
		ER90 S-G	QT	160-220	560-640	
G20MnMo4	4.2	ER120 S-G	SR	300-360	900-950	
		ER120 S-G	QT	280-360	920-1020	


111 : Electrode welding
135 : MAG

SR : Stress relieving
QT : Quenched and Tempered

N : Normalized

Comparative Table of Safe Metal grade

C-Mn	Chemical composition								N			QT (Q&T20°C)			
	C (%)	Mn (%)	Si (%)	Cr (%)	Mo (%)	V (%)	Ni (%)	Ceq (%)	Rm	AN	Kv (-20°C)	Rm	AN	Kv (-20°C)	
C25	0,2	0,7	0,45					0,32	440	25	22	420-520	20-25	40-50	
GE240	0,23	0,9	0,5					0,4	480	25	12	520-660	25-30	oct-20	
GE280	0,24	1,2	0,5	0,15				0,47	530	20	10	600-860	15-25	20-40	
G20MnS (low)	0,2	1,1	0,4					0,38	470	28	40	500-590	20-22	38-46	
G20MnS (high)	0,23	1,4	0,5					0,5				600-680	dec-23	25-30	
G20MnV6	0,23	1,55	0,5			0,05		0,54	580	25	10				
G24MnS (low)	0,23	1,65	0,5					0,52	590	18	10	550-670	20-25	40-75	
G24MnS (high)	0,25	1,8	0,5					0,6	630	32	10	620-900	oct-25	15-35	
G28Mn6	0,3	1,4	0,5					0,53	650	17	10	650-840	oct-15	30-60	
G30MnV6	0,3	1,4	0,5			0,1		0,55	650	12	30	700-950	05-dec	30-45	
Chemical composition										N			QT (Q&T20°C)		
Cr-Mo	C (%)	Mn (%)	Si (%)	Cr (%)	Mo (%)	V (%)	Ni (%)	Céq. (%)	Rm	AN	Kv (-20°C)	Rm	AN	Kv (-20°C)	
G18CrMo4	0,18	0,8	0,4	1	0,2			0,35	430	18	10	500-720	dec-22	30-80	
G25CrMo4	0,25	0,8	0,4	1	0,2			0,62	600	11	12	600-950	oct-18	20-90	
G30CrMo4	0,3	0,8	0,4	1	0,2			0,67	840	5	10	650-1050	oct-18	20-90	
G21CrMoV5-11	0,2	0,7	0,5	1,15	1	0,3		0,82	980	5	5	900-1200	05-oct	5	
Chemical composition										N			QT (Q&T20°C)		
Others	C (%)	Mn (%)	Si (%)	Cr (%)	Mo (%)	V (%)	Ni (%)	Céq. (%)	Rm	AN	Kv (-20°C)	Rm	AN	Kv (-20°C)	
G10MnMoV6	0,12	1,35	0,5			0,08		0,42	460	17	10	500-750	14-16	20-50	
G20MnMoV4	0,18	1	0,4	0,4	0,6		0,3	0,62	730	5	10	600-950	dec-20	35-100	



Family : Versatile



Family : Versatile



© 2000 Blackwell Science Ltd



GROWTH




Family : Verceatile



024W110



Family : Versatile



Family : Verceutile



Family : High resistance



Family : High resistance




Family : High resistance



Family : High resistance



Family : Special



Family : Special



Family : Cast iron



